



Certified to NSF/ANSI/CAN 60



ENVIROPLUG® GROUT

Product Information

Description

ENVIROPLUG® GROUT is a patented formula bentonite product designed to be used as a water well grouting fluid, drill hole abandonment fluid, grout for geotechnical monitoring wells after casing placement, and other geotechnical construction applications requiring non-destructible sub-grade seals. Once in place, **ENVIROPLUG® GROUT** begins to set and assumes a caulk-like consistency that contacts formations to establish a low permeability seal (1 X 10⁻⁹ cm/sec).

Characteristics

- Dry Fineness: 80% min. passing a 200 mesh screen
- Processed Bulk Density: 58.0 ± 4 pounds/cubic foot
- pH: 5% slurry, 8 to 9.8
- Density: 10.2 pounds/gallon at 30% solids
- Permeability: 1 x 10⁻⁹ cm/sec
- Thermal Conductivity 0.43 Btu/hr-ft-°F

Application

- **ENVIROPLUG® GROUT** can be mixed and placed using most available pumping equipment. Although paddle type mixers and positive displacement pumps work best.
- Maximum performance is achieved at a ratio of 1 bag to 14 gallons of water (30% solids). Since pumps such as double diaphragm or gear pumps may not produce enough pressure to place highly viscous mixtures, the ratio can be adjusted to 1 bag per 16 gallons of water and still achieve a good grout "set".
- As **ENVIROPLUG® GROUT** is added to the make-up water, a "pan-cake batter" consistency is generated. Pumping at this time is recommended as it minimizes migration into formations and allows for continued hydration to take place down hole.
- Provided local regulations allow, it is always recommended to withdraw the tremie line as grout is being pumped. This permits the grout to continue its "set" undisturbed, reduces pump pressure and minimizes unnecessary migration into formations.

Mixing Ratios			
Dry Grout	Water	Usable Slurry	Solids Content
50 lb	14 gal	17 gal	30.0%
50 lb	15 gal	18 gal	28.6%
50 lb	16 gal	19 gal	27.3%

TYPICAL CHEMICAL ANALYSIS %					
SiO ₂	61.4	MnO	0.10	TiO ₂	0.20
Al ₂ O ₃	18.1	MgO	1.70	Na ₂ O	2.30
Fe ₂ O ₃	3.50	CaO ₃	0.40	H ₂ O	4.50
K ₂ O	0.10				
L.O.I. *	4.37	*Loss on Ignition			

TYPICAL E.P. TOXICITY ANALYSIS		
	Standard (ppm)	Set Grout (ppm)
Arsenic	5.0	<0.10
Barium	100.0	0.50
Cadmium	1.0	<0.05
Chromium	5.0	<0.10
Lead	5.0	<0.10
Mercury	0.2	<0.02
Selenium	1.0	<0.05
Silver	5.0	<0.10

Packaging

ENVIROPLUG® GROUT is packaged in 50 pound bags.

4250/201302

WYO-BEN, INC., Billings, Montana

800.548.7055

406.652.6351

www.wyoben.com

The information and data made herein are believed to be accurate. As Wyo-Ben, Inc. has no control over use or application of this product, it is sold without warranty or guarantee of results.